

导热矽胶

品名 型号	厚度 (mm)	耐温度(°C)	热传导系数 (W / M-K)	热组抗°C / W	基材
SJT-3G	0.5~1.0T	-40°C~200°C	3.2	1.12	Silcone
SJT-3Y	0.5~1.0T	-40°C~200°C	2.3	1.14	Silcone
SJT-4G	0.5~1.0T	-40°C~200°C	2.8	1.2	Silcone
SJT-4Y	0.5~1.0T	-40°C~200°C	2.8	1.2	Silcone
SJT-5G	0.16T	-40°C~200°C	0.95	0.38	Silcone
SJT-5Y	0.16T	-40°C~200°C	1.3	0.23	Silcone
SJT-4G-A	0.2~0.8T	-40°C~200°C	1.4	1.2	Silcone
SJT#1800	0.18T	-35°C~140°C	1.5		AL
SJT#2500	0.25T	-35°C~140°C	1.8		AL
SJT#3000	0.30T	-35°C~140°C	2.5		FIBER GLASS



产品特性：

具耐高温、高粘著力，以矽胶、铝材、玻纤为基材
不同材料链结产品，具有缓冲作用及显著导热效果。

适用范围：

应用於粘著发热元件与散热片、CPU。

